


Technical Data Sheet
Edition 4, 2008
Identification no.
02 04 01 02 001 0 000025
Version no. 0010
SikaWrap® -230 C/45

SikaWrap® -230 C/45

Woven carbon fiber fabric for structural strengthening

Product Description	SikaWrap® -230 C/45 is a unidirectional woven carbon fiber fabric for the dry application process.	
----------------------------	--	---

Uses	<p>Strengthening of reinforced concrete structures, brickwork and timber in case of flexural and shear load due to :</p> <ul style="list-style-type: none"> ■ Improved seismic performance of masonry walls. ■ Substitute missing rebars. ■ Strength and ductility of columns. ■ Increasing loading capacity of structural elements. ■ Changes of building utilisation. ■ Structural design construction defects ■ Seismic movement. ■ Improved serviceability. ■ Structural upgrading to comply with current standards.
-------------	---

Characteristic / Advantages	<ul style="list-style-type: none"> ■ Manufactured with weft fibers to keep the fabric stable (heat-set process) ■ Multifunctional use for every kind of strengthening requirement. ■ Flexibility of surface geometry (Beams, columns, chimneys, piles, walls, silos) ■ Fabric available in several widths for optimum utilisation. ■ Low density for minimal additional weight. ■ Economical compared to traditional techniques.
------------------------------------	--

Product Data

Form	
Fiber Type	Mid strength carbon fibers

Fabric Construction	<p>Fiber orientation: 0° (unidirectional) Warp: black carbon fibers (99% of total areal weight) Weft : white thermoplastic heat-set fibers (1% of total areal weight)</p>
----------------------------	---

Packaging		Fabric length /roll	Fabric width
	1 roll in cardboard box	≥ 50 m	300 / 600 mm

Storage	
Storage Conditions / Shelf Life	24 months from date of production if stored properly in undamaged original sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight.




Table of contents

Technical Data

Areal Weight 230 g/m² ± 10 g/m²

Fabric Design Thickness 0.131 mm (based on fiber content)

Fiber Density 1.76 g/cm³

Mechanical / Physical Properties

Dry Fiber Properties

Tensile strength:
4'300 N/mm² (nominal)

Tensile E-modulus:
238'000 N/mm² (nominal)

Elongation at break:
1.8% (nominal)

Laminate Properties

Laminate thickness:
1.0 mm per layer (impregnated with Sikadur[®]-330)

Ultimate load:
350 kN/m width per layer (at typical laminate thickness of 1.0 mm)

Tensile E-modulus:
28.0 kN/mm² (based on typical laminate thickness of 1.0 mm)

Note:
The above values are typical and indicative only.
The achievable laminate properties obtained from tensile test are dependant on the impregnating/laminating resin used and the type of tensile testing procedure.
Apply material reduction factors according to the relevant design standard.

Design

Design strain
Max. 0.75% (this value is dependent on the type of loading and must be adapted according to the relevant local design standards)

Tensile strength: (theoretical tensile strength for the design):

- at elongation 0.4%: 100 kN/m width (= 30 kN / 30 cm)
(= 60 kN / 60 cm)
- at elongation 0.6%: 150 kN/m width (= 45 kN / 30 cm)
(= 90 kN / 60 cm)

System Information

System Structure

The system configuration as described must be fully complied with and may not be changed.

Concrete primer -Sikadur[®]-330

Impregnating / laminating resin -Sikadur[®]-330

Structural strengthening fabric -SikaWrap[®]-230 C/45.

For detailed resin properties, fabric application details and general information, refer to Sikadur[®]-330 Product Data Sheet.

Application Details

Consumption

Depending on the roughness of the substrate.

- Impregnating of the first layer incl. primer: ~ 0.7 -1.2 kg/m² (Sikadur[®]-330)
- Impregnating of the following layers: ~ 0.5 kg/m² (Sikadur[®]-330)

Substrate Quality

Specific requirements:
Minimal substrate tensile strength: 1.0 N/mm² or as specified in the strengthening design.

Substrate Preparation Refer to Sikadur[®]-330 Product Data Sheet

Application Instructions	
Application Method / Tools	The fabric can be cut with special scissors or razor knife. Never fold the fabric! Refer to Sikadur® -330 Product Data Sheet for impregnating / laminating procedure.
Notes on Application / Limitations	<p>This product may only be used by experienced professionals.</p> <p>Minimum radius required for application around corners: >10 mm. Grinding edges or building up with Sikadur® mortars may be necessary.</p> <p>In fiber direction, overlapping of the fabric must be at least 100 mm depending on SikaWrap® type or as specified in the strengthening design.</p> <p>For side-by-side application, no overlapping length in the weft direction is required. Overlaps of additional layers must be distributed over the column circumference.</p> <p>The strengthening application is inherently structural and great care must be taken when choosing suitably experienced contractors.</p> <p>The SikaWrap® -230 C/45 fabric is coated to ensure maximum bond and durability with the Sikadur® impregnating/laminating resins. To maintain system compatibility do not interchange system parts.</p> <p>The SikaWrap® -230 C/45 may be / must be coated with a cementitious overlay or coatings for aesthetic and/or protective purposes. Selection will be dependent on exposure requirements. For basic UV protection use Sikagard® -550 W Elastic, Sikagard® ElastoColor-675 W or Sikagard® -680 S.</p>
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	<p>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request</p>



PT. Sika Indonesia
 Jl. Raya Cibinong- Bekasi km. 20
 Limusnunggal- Cileungsi
 BOGOR 16820 - Indonesia
 Tel. +62 21 8230025
 Fax +62 21 8230026
 Website : www.sika.co.id
 e-mail: sikacare@id.sika.com

Branches
 Surabaya :
 Puri Niaga Blok G No. 29, Jl. Raya Rungkut Menanggal 11, Surabaya
 Tel : 031-8690202 ; Fax : 031-8682123
 Medan :
 Jl. Pancing / Jl. Willem Iskandar No.75 & 75 A, Kec. Medan Tembung
 Tel : 061- 6619500; Fax : (061) 6619400
 Batam :
 Jl. Laksamana Bintan, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas
 Tel : (0778) 424928; Fax : (0778) 450189

