

Nitobond AR

Acrylic emulsion bonding agent for concrete repairs

Uses

Recommended primer for the Renderoc Cementitious Repair System.

Advantages

- Single component gauged as required
- Simply brushed onto concrete as a primer
- Provides excellent bond to concrete, masonry, stonework, plaster and blockboard
- Suitable for use in tropical conditions
- Can also be used as a curing membrane for localised patch repairs
- Is economical in use

Description

Nitobond AR is a modified acrylic emulsion, specially designed for use as a bonding aid and curing agent for concrete repair systems. It is resistant to hydrolysis and can therefore be used for external application.

Standards compliance

BS 6920 - Approved for use with potable water

Technical support

Fosroc offers a comprehensive range of high performance, high quality construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Properties

Adhesion to concrete – Slant shear bond test
(BS 6319 Pt 4; 1984)

Control	:	5.0 N/mm ²
Curing efficiency BS 7542: 1992	:	> 55%

Instructions for use

Surface preparation

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Where breaking out is not required, roughen the surface and remove any laitance by light scabbling or grit-blasting.

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to bright condition paying particular attention to the back of the exposed steel bars. Grit-blasting is recommended for this process.

Reinforcing steel priming

Apply one full coat of Nitoprime Zincrich to all exposed steel reinforcement and allow to dry prior to continuing. If any doubt exists about having achieved an unbroken film, a second application should be made and allowed to dry prior to continuing.

Application of bonding aid

The substrate should be thoroughly soaked with clean water with any excess removed prior to commencement of the works. Scrub Nitobond AR into the substrate, avoid ponding and remove any excess. The repair mortar or topping should be applied whilst the primer is still tacky.

Curing

Cure the repair mortar or topping using Nitobond AR to prevent rapid loss of water. In severe drying conditions additional curing methods may be necessary. Protect uncured mortar from frost and rain.

Cleaning

Nitobond AR should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Nitobond AR

Limitations

Nitobond AR mortars, toppings and renders should not be used when the temperature is below 5°C and falling, neither should they be exposed to moving water during application.

Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature, application or substrate conditions, consult the local Fosroc office.

Estimating

Supply

Nitobond AR	:	5, 20 & 200 Litre
-------------	---	-------------------

Coverage and yield

Nitobond AR :	:	6 - 8 m ² / litre as a primer
	:	4 to 5 m ² /litre as curing agent

Storage

Shelf life

All products have a shelf life of 6 months at 20°C if kept in a dry store in the original, unopened containers.

Precautions

Health and safety

Cementitious mortars modified with Nitobond AR contain cement powders which, when mixed or become damp release alkalis which can be harmful to skin. During use avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves and eye/face protection.

The use of barrier creams provide additional skin protection. Should accidental skin contact occur, remove immediately with a resin removing cream followed by soap and water. Do **not** use solvent.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately – do **not** induce vomiting.

Fire

Nitobond AR is non-flammable.



Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8
Seksyen 33, 40400 Shah Alam
Selangor, Malaysia

Branch Office:

215B Argyll Rd, 10050 Penang
Malaysia

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+60 3 5191 5660

fax:
+60 3 5191 6960

email:
malaysia@fosroc.com

+60 4 228 7464

+60 4 228 0901



2413-2005-AQ-SIN-
RVA