

Nitoflor SL2000

Flow applied, 2mm thick epoxy resin based floor topping

Uses

Nitoflor SL2000 is designed for use in a wide range of light industrial environments where a lasting solution to floor maintenance problems is required. It provides a dense, impervious, coloured and chemically resistant floor surface which is hygienic and easy to clean.

Typical applications include clean rooms, laboratories, plant rooms, light industrial plants, pharmaceutical and electronic industries.

Advantages

- Fast application - minimises downtime
- Chemically resistant - good resistance to a wide range of chemicals
- Durable - good abrasion resistance
- Hygienic - provides a dense, impervious, seamless floor surface which is easily cleaned
- Solvent free - non tainting
- Attractive - available in a wide range of colours to enhance the working environment

Standard Compliance

Nitoflor SL2000 has been tested in accordance with BS 4247, Part 1 Nuclear Decontamination parts A and B. In both instances a "good" classification was obtained.

Description

Nitoflor SL2000 consists of graded aggregates bound in a pigmented epoxy resin binder. It is supplied as a three component system, pre-weighed for on-site mixing.

Nitoflor SL2000 is applied at 2-2.5 mm thickness and when laid, it provides a smooth, light-reflective surface. It is available in a wide range of standard colours..

Technical Support

Fosroc offers a comprehensive range of high performance, high quality, flooring, jointing and repair products for both new and existing floor surfaces.

In addition, the company offers a technical support package to specifiers, end-users and contractors, as well

as on-site technical assistance in locations all over the world.

In areas where significant thermal shock is likely to occur, consult the local Fosroc office.

Nitoflor SL2000 should not be applied to asphalt, weak or friable concrete, PVC tiles or sheet or substrates known to move substantially e.g. steel walkways. For information on other substrates, consult the local Fosroc office.

Chemical properties

Nitoflor SL2000 has good resistance at ambient temperatures to a wide range of industrial chemicals. Specific data is available on request.

Note that it is especially important that spillage is cleaned up quickly since much higher concentrations of chemicals may occur on evaporation.

For details of other chemicals, please contact your local Fosroc office.

Properties

The values given below are average figures achieved in laboratory tests at 25°C. Actual values obtained on site may show minor variations from those quoted.

Physical properties

Compressive strength	
(BS 6319) :	50N/mm2 @7days
Flexural strength	
(BS 6319) :	34 N/mm2@7days
Abrasion resistance	
(ASTM-D4060-95):	2.42gm (0.45%) after 1000 cycles
Bond strength :	Failure at concrete substrate
Cure time –	
Foot traffic :	24 hours
Vehicular traffic :	48 hours
Chemical :	7 days

Chemical properties

Nitoflor SL2000 has excellent resistance at ambient temperatures to a wide range of industrial chemicals. Specific data is available on request.

Nitoflor SL2000

Design criteria

Nitoflor SL2000 is designed for application at a nominal thickness of between 0.5 - 1.5mm.

Substrates should be dry and not suffer, or be likely to suffer, from rising damp. If necessary, suitable damp-proof membranes should be installed to prevent this.

Substrates **should not** have a relative humidity greater than 75% at the time of installation.

Specification clauses

Flow-applied epoxy floor topping

The designated floor areas shall be surfaced with Nitoflor SL2000, a 2mm thick flow-applied epoxy resin floor topping. The topping shall achieve a compressive strength of 50 N/mm² and a flexural strength of 34 N/mm² at 7 days when tested to BS 6319. At 250C, it shall be capable of accepting foot traffic at 24 hours and vehicular traffic at 48 hours.

Instructions for use

Nitoflor SL2000 should be applied by specialist applicators who must follow the procedures laid down in the product method statement. Fosroc works with a network of such applicators that have been trained in the correct installation procedures.

The following steps are involved in the application which would normally take place over a 2 to 3 day period.

Surface Preparation

It is essential that Nitoflor SL2000 is applied to clean, sound and dry surfaces in order that maximum bond strength is achieved between the substrate and the flooring system. All dust and debris should be removed prior to application of the product and its primer.

New concrete surfaces

New concrete, or cementitious substrates, should be at least 28 days old and have a moisture content not exceeding 5%. Laitance deposits on new concrete are best removed by light grit blasting, mechanical scabbling or grinding.

Old concrete surfaces

Existing concrete floors which require refurbishment must be prepared to ensure a strong adhesive bond between

the flooring system and the existing floor. Mechanical cleaning methods are strongly recommended, particularly where heavy contamination by oil and grease has occurred or existing coatings are present. To ensure adhesion, all contamination should be removed. Proprietary chemical degreaser may be used on small areas of light contamination only.

Steel surfaces

Steel surfaces should be degreased and grit blasted to SA2½ immediately prior to application. The prepared surface should then be primed with one coat of Nitocote Primer Sealer.

Priming

All surfaces treated with Nitoflor SL2000 should be primed with Nitoprime 25, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates.

Add the entire contents of the hardener tin to the base tin and mix the two primer components thoroughly for at least 2 minutes - under no circumstances should part mixing be considered.

Once mixed, the primer should be applied immediately to the prepared substrate using stiff brushes and/or rollers. The primer should be well 'scrubbed' into the substrate to ensure full coverage, but care should be taken to avoid over unsightly application or 'ponding'.

Allow the primer to dry (see table below) before proceeding to the next stage. Do not proceed whilst the primer is 'tacky' as this will lead to unsightly marks in the finished surface.

Porous substrates may require a second primer coat - when the first coat is directly absorbed into the substrate - but minimum overcoating times must still be observed (see table below).

The minimum overcoating times will vary slightly according to the porosity of the substrate. However, they should be in accordance with the following ambient application temperatures.

20°C	:	8 - 12 hours
30°C	:	6 - 8 hours
40°C	:	4 - 6 hours

Nitoflor SL2000

Mixing

Nitoflor SL 2000 flooring is supplied in four pre-weighed packs (base, hardener, aggregate and colour pack) which are ready for immediate on-site use. Part mixing of these components is not acceptable and will affect both performance and appearance of the finished floor, and would furthermore automatically invalidate Fosroc's standard product guarantee.

Mixing should be carried out using either a forced action mixer; or a heavy duty, slow-speed drill with proprietary mixing paddle attachment. All such equipment should be of a type and capacity approved by Fosroc. The components should be mixed in a suitably sized mixing vessel.

The colour pack should be added to the base container and mixed for 15-30 seconds, until homogeneous. Then add the hardener and mix for further 30 seconds, until an even colour and texture is obtained.

Thereafter, the contents of the graded aggregate pack should be slowly added and mixing carried out for a further 3 minutes until a completely homogeneous material is obtained.

Application

The applicator should ensure that there are sufficient supplies of plant, labour and materials to make the mixing and subsequent application process a continuous one for any given, independent floor area.

Once mixed, the material must be used within its specified pot life - see "**Properties**" section.

The material should be poured onto the prepared and primed substrate as soon as mixing is complete. It should be spread to the required thickness preferably using a pin screed, if not a serrated trowel; with care taken not to overwork the resin, spreading evenly and slowly.

Immediately after laying, the material should be rolled, using a spiked nylon roller, to remove slight trowel marks, and to assist air release. The rolling should be carried out using a 'back and forth' technique along the same path. An overlap of 50% with adjacent paths is recommended.

The rolling process should continue for a minimum of 5 times on the same path, but should be prior to setting of the product.

Floor joints

All existing expansion or movement joints should be followed through the new floor surface.

Joint sealant & joint geometry should be compatible with the floor type used, intended exposure conditions and likely movement characteristics of the substrate - consult Fosroc for more details.

Cleaning

Nitoprime 25 and Nitoflor SL2000 should be removed from tools and equipment with Fosroc Solvent 102 immediately after use. Hardened material can only be removed mechanically.

Maintenance

The service life of a floor can be considerably extended by good housekeeping. Regular cleaning may be carried out using a rotary scrubbing machine with a water miscible cleaning agent at temperatures up to 50°C.

Estimating

Supply

Nitoflor SL2000	:	12 litre packs
-----------------	---	----------------

Priming and Cleaning Products :

Nitoprime 25	:	5 kg packs
--------------	---	------------

Fosroc Solvent 102	:	5 litre cans
--------------------	---	--------------

Coverage

Nitoflor SL2000	:	6 m ² /pack @ 2 mm thickness
-----------------	---	---

Nitoprime 25	:	5 m ² /kg
--------------	---	----------------------

Note : The coverage figures given are theoretical - due to wastage factors and variety and nature of possible substrates, practical coverage figures will be reduced. Typically, an additional 10% should be allowed for surface irregularities and wastage although this will vary with site conditions.

Nitoflor SL2000

Storage

Shelf life

All products have a shelf life of 12 months if kept in a dry store in the original, unopened packs.

Storage conditions

Store in dry conditions between 5°C and 30°C, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures the shelf life may be reduced.

Precautions

Health and safety

Nitoflor SL2000, Nitoprime 25 and Fosroc Solvent 102 should not come into contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents.

Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent.. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Fire

Nitoprime 25 and Fosroc Solvent 102 are flammable materials. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO₂ or foam. Do not use a water jet.

Flash points

Nitoprime 25	:	39°C
Fosroc Solvent 102	:	33°C

Disposal

Spillages of component products should be absorbed onto earth, sand or other inert material and transferred to a suitable vessel. Disposal of such spillages or empty packaging should be in accordance with local waste disposal regulations.

For further information, refer to the Product Material

Additional information

A technical note relating to the survey and preparation guidelines for resin floor installation is available. Please request from the local Fosroc office.

Fosroc manufactures a wide range of products specifically designed for the specialist flooring industry. These include liquid-applied, chemically-resistant coatings, self-levelling epoxy toppings and trowel-applied, highly abrasion resistant screeds.



Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8
Seksyen 33, 40400 Shah Alam
Selangor, Malaysia

Branch Office:

215B Argyll Rd, 10050 Penang
Malaysia

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+60 3 5191 5660

fax:
+60 3 5191 6960

email:
malaysia@fosroc.com

+60 4 228 7464

+60 4 228 0901



2413-2005-AQ-SIN-
RVA