


## **Sikadur® 31 CF Normal (formerly Sikadur 731)**

### 2-part thixotropic epoxy adhesive

<b>Product Description</b>	Sikadur®-31 CF Normal is a solvent-free, moisture tolerant, thixotropic, structural two part adhesive and repair mortar, based on a combination of epoxy resins and special fillers, designed for use at temperatures between +10°C and +30°C.
<b>Uses</b>	<p>As a structural adhesive and mortar for :</p> <ul style="list-style-type: none"><li>■ Concrete elements</li><li>■ Hard natural stone</li><li>■ Ceramics, fiber cement</li><li>■ Mortar, Bricks, Masonry</li><li>■ Steel, Iron, Aluminium</li><li>■ Wood</li><li>■ Polyester, Epoxy</li><li>■ Glass</li></ul> <p>As a repair mortar and adhesive:</p> <ul style="list-style-type: none"><li>■ Corners and edges</li><li>■ Holes and void filling</li><li>■ Vertical and overhead use</li></ul> <p>Joint filling and crack sealing:</p> <ul style="list-style-type: none"><li>■ Joint and crack arris / edge repair</li></ul>
<b>Characteristics / Advantages</b>	<p>Sikadur®-31 CF Normal has the following advantages:</p> <ul style="list-style-type: none"><li>■ Easy to mix and apply</li><li>■ Suitable for dry and damp concrete surfaces</li><li>■ Very good adhesion to most construction materials</li><li>■ High strength adhesive</li><li>■ Thixotropic: non-sag in vertical and overhead applications</li><li>■ Solvent free</li><li>■ Hardens without shrinkage</li><li>■ Different coloured components (for mixing control)</li><li>■ No primer needed</li><li>■ High initial and ultimate mechanical strength</li><li>■ Good abrasion resistance</li><li>■ Impermeable to liquids and water vapour</li><li>■ Good chemical resistance</li></ul>
<b>Tests</b>	
<b>Approval / Standards</b>	Testing according to ASTM, C881M-02, Type I, Grade 3, Class B+C. Testing according to EN 1504-4.
<b>Product Data</b>	
<b>Form</b>	
<b>Colours</b>	Part A: white Part B: dark grey Parts A+B mixed: concrete grey



[Table of contents](#)

<b>Packaging</b>	6 kg (A+B) Pre-batched unit			
<b>Storage</b>				
<b>Storage Conditions/ Shelf-Life</b>	24 months from date of production if stored properly in original unopened, sealed and undamaged packaging, in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunshine.			
<b>Technical Data</b>				
<b>Chemical Base</b>	Epoxy resin.			
<b>Density</b>	1.90 + 0.1 kg/l (part A) (at +23°C) 1.90 + 0.1 kg/l (part B) (at +23°C) 1.90 + 0.1 kg/l (part A+B mixed) (at +23°C) (evacuated)			
<b>Sag Flow</b>	On vertical surfaces it is non-sag up to 15 mm thickness. (according to EN 1799)			
<b>Layer Thickness</b>	30 mm max.  When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.			
<b>Change of Volume</b>	Shrinkage: Hardens without shrinkage.			
<b>Thermal Expansion Coefficient</b>	Coefficient W: 59 x 10 <sup>-6</sup> per °C (Temp. range +23°C - +60°C)		(according EN 1770)	
<b>Thermal Stability</b>	Heat Deflection Temperature (HDT): HDT = +49°C (7 days / +23°C)		(according to ISO 75) (thickness 10 mm)	
<b>Mechanical / Physical Properties</b>				
<b>Compressive Strength</b>	(according to DIN EN 196)			
	Curing time	+10°C	+23°C	+30°C
	1 day	25 – 35 N/mm <sup>2</sup>	45 – 55 N/mm <sup>2</sup>	50 – 60 N/mm <sup>2</sup>
	3 days	40 – 50 N/mm <sup>2</sup>	55 – 65 N/mm <sup>2</sup>	60 – 70 N/mm <sup>2</sup>
	7 days	50 – 60 N/mm <sup>2</sup>	60 – 70 N/mm <sup>2</sup>	60 – 70 N/mm <sup>2</sup>
<b>Flexural Strength</b>	(according to DIN EN 196)			
	Curing time	+10°C	+23°C	+30°C
	1 day	11 – 17 N/mm <sup>2</sup>	20 – 30 N/mm <sup>2</sup>	20 – 30 N/mm <sup>2</sup>
	3 days	20 – 30 N/mm <sup>2</sup>	25 – 35 N/mm <sup>2</sup>	25 – 35 N/mm <sup>2</sup>
	7 days	25 – 35 N/mm <sup>2</sup>	30 – 40 N/mm <sup>2</sup>	30 – 40 N/mm <sup>2</sup>
<b>Tensile Strength</b>	(according to ISO 527)			
	Curing time	+10°C	+23°C	+30°C
	1 day	2 – 6 N/mm <sup>2</sup>	6 – 10 N/mm <sup>2</sup>	9 – 15 N/mm <sup>2</sup>
	3 days	9 – 15 N/mm <sup>2</sup>	17 – 23 N/mm <sup>2</sup>	17 – 23 N/mm <sup>2</sup>
	7 days	14 – 20 N/mm <sup>2</sup>	18 – 24 N/mm <sup>2</sup>	19 – 25 N/mm <sup>2</sup>
<b>Bond Strength</b>	(according to EN ISO 4624, EN 1542 and EN 12188)			
	Curing time	Temperature	Substrate	Bond strength
	1 day	+10°C	Concrete dry	> 4 N/mm <sup>2</sup> *
	1 day	+10°C	Concrete moist	> 4 N/mm <sup>2</sup> *
	1 day	+10°C	Steel	6 – 10 N/mm <sup>2</sup>
	3 days	+10°C	Steel	10 – 14 N/mm <sup>2</sup>
	3 days	+23°C	Steel	11 – 15 N/mm <sup>2</sup>
	3 days	+30°C	Steel	13 – 17 N/mm <sup>2</sup>

\*100% concrete failure.

<b>E-Modulus</b>	Tensile: ~ 5'000 N/mm <sup>2</sup> (14 days at +23°C) (according to ISO 527) Compressive: ~ 4'600 N/mm <sup>2</sup> (14 days at +23°C) (according to ASTM D695)
<b>Elongation at Break</b>	0.4 ± 0.1% (7 days at +23°C) (according to ISO 75)
<b>Strength Development</b>	Confirm the strength development by producing cubes on site and testing them for compressive and flexural strength.

## System Information


### Application Details

<b>Consumption / Dosage</b>	The consumption of Sikadur <sup>®</sup> -31 CF Normal is ~ 1.9 kg/m <sup>2</sup> per mm of thickness.
<b>Substrate Quality</b>	Mortar and concrete must be older than 28 days (dependent on environment and strength). Verify the substrate strength (concrete, masonry, natural stone). The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc. Steel substrates must be de-rusted similar to SA 2.5. The substrate must be sound and all loose particles must be removed.
<b>Substrate Preparation</b>	Concrete, mortar, stone, bricks: Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and loosely adhering particles to achieve a laitance and contaminant free, open textured surface. Steel: Must be cleaned and prepared thoroughly to an acceptable quality i.e. by blastcleaning and vacuum. Avoid dew point conditions.  Other surfaces (polyester, epoxy, glass, ceramic): On these substrates pre-apply Sikafloor <sup>®</sup> -156 (primer) and then, "wet on wet" apply Sikadur <sup>®</sup> -31 CF Normal.

### Application Conditions / Limitations

<b>Substrate Temperature</b>	+10°C min. / +30°C max.
<b>Ambient Temperature</b>	+10°C min. / +30°C max.
<b>Material Temperature</b>	Sikadur <sup>®</sup> -31 CF Normal must be applied at temperatures between +10°C and +30°C
<b>Substrate Humidity</b>	When applied to mat moisture concrete, brush the adhesive well into substrate.
<b>Dew Point</b>	Beware of condensation! Ambient temperature during application must be at least 3°C above dew point.

### Application Instructions

<b>Mixing</b>	Part A : part B = 2 : 1 by weight or volume
<b>Mixing Time</b>	 <p>Pre-batched units Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.</p>

### Application Method / Tools

When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves).  
When applying as a repair mortar use some formwork.  
When using for bonding metal profiles onto vertical surfaces, support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 mm) and the room temperature.  
Once hardened check the adhesion by tapping with a hammer.

<b>Cleaning of Tools</b>	Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardener / cured material can only be mechanically removed.						
<b>Potlife</b>	Potlife (200 g)						
	<table border="1"> <thead> <tr> <th>+10°C</th> <th>+23°C</th> <th>+30°C</th> </tr> </thead> <tbody> <tr> <td>~ 145 minutes</td> <td>~ 55 minutes</td> <td>~ 35 minutes</td> </tr> </tbody> </table>	+10°C	+23°C	+30°C	~ 145 minutes	~ 55 minutes	~ 35 minutes
	+10°C	+23°C	+30°C				
~ 145 minutes	~ 55 minutes	~ 35 minutes					
The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C).							
<b>Value Base</b>	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.						
<b>Protective Measures</b>	To avoid rare allergic reactions, use of protective gloves. Changes soiled work clothes and wash hands before breaks and after finishing work. When uncured, Sikadur®-31 CF Normal parts A+B, are water-pollutants and must not be discharge into drains, waterways or the ground.  Local regulation as well as health and safety advice on packaging labels must be observed.						
<b>Important Notes</b>	Uncured / unmixed material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.  Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the material safety data sheet.						
<b>Legal Notes</b>	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request						



**PT. Sika Indonesia**  
 Jl. Raya Cibinong- Bekasi km. 20  
 Limusunggal- Cileungsi  
 BOGOR 16820 - Indonesia  
 Tel. +62 21 8230025  
 Fax +62 21 8230026  
 Website : [www.sika.co.id](http://www.sika.co.id)  
 e-mail: [sikacare@id.sika.com](mailto:sikacare@id.sika.com)

**Branches**  
 Surabaya :  
 Puri Niaga Blok G No. 29, Jl. Raya Rungkut Menanggal 11, Surabaya  
 Tel : 031-8690202 ; Fax : 031-8682123  
 Medan :  
 Jl. Pancing / Jl. Willem Iskandar No.75 & 75 A, Kec. Medan Tembung  
 Tel : 061- 6619500; Fax : (061) 6619400  
 Batam :  
 Jl. Laksamana Bintan, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas  
 Tel : (0778) 424928; Fax : (0778) 450189

